

**MODENA CENTRO PROVE s.r.l.**

Sede legale e Laboratori: 41123 Modena (Italy) - Via Sallustio, 78
Tel. 059 822417 r.a. - Fax 059380281 - e-mail : info@modenacentroprove.it - www.modenacentroprove.com
C.C.I.A.A. Modena n. 228587 - Tribunale di Modena n° 2231 - C.F. e P. IVA n. 01592020364

MECCANICA

ECOLOGIA

CERAMICA

ALIMENTARE

Modena, 05/08/19

To **CERAMIKA NOWA GALA S.A.**
UL. CERAMICZNA 1
26-200 KONSKIE PL

Attn.

MATERIAL and/or SAMPLE to be tested	Denomination of the Sample	Client Reference – Your delivery	date
	STONEHENGE NATURA (SH NAT.)	VS CONSEGNA	31/07/2019

Here attached, you will receive the Test Report of Serial No. **20195354**/n, which shows the results of tests required.

MODENA CENTRO PROVE

MODENA CENTRO PROVE

Director
Sant'Unione dr. Giuseppe



MODENA CENTRO PROVE s.r.l.

Sede legale e Laboratori: 41123 Modena (Italy) - Via Sallustio, 78
Tel. 059 822417 r.a. - Fax 059380281 - e-mail : info@modenacentroprove.it -
www.modenacentroprove.com
C.C.I.A.A. Modena n. 228587 - Tribunale di Modena n° 2231 C.F. e P. IVA n. 01592020364



LAB N°1018L

Membro degli Accordi di Mutuo Riconoscimento EA, IAF e ILAC

Signatory of EA, IAF and ILAC Mutual Recognition Agreements

TEST REPORT: 20195354/1

Modena, 05/08/19

CUSTOMER	CERAMIKA NOWA GALA S.A. - - UL. CERAMICZNA 1 - 26-200 - KONSKIE - PL
MATERIAL and/o SAMPLE to be tested	;
Denomination	STONEHENGE NATURA (SH NAT.);
Date of sample reception	31/07/2019;
Date of sample acceptance	31/07/2019;
Kind of test executed	Determination of the anti-slip properties – Wet-loaded barefoot areas; Walking method – Ramp test
Referring standards	DIN 51097:1992
Shifting from standards	No one
Equipment	Pullmeter with ramp cod. MCP C150
Subcontracted phases	No one
Sampling made by	Customer

*The test results showing in this Report are only referred to the sample taken by our staff or supplied by the Customer. He commits himself to reproduce integrally this document. Partial reproduction is forbidden.
The times of retain of the samples was indicated in the offer related to the test report.*

Examiner p.i. Bortolai Alberto	Examiner p.i. Nasseti Luca	MODENA CENTRO PROVE Ceramic Dept. Responsible P.I. De Pasquale Roberto	MODENA CENTRO PROVE Director Sant'Unione dr. Giuseppe
--	--	---	--



MODENA CENTRO PROVE s.r.l.

Sede legale e Laboratori: 41123 Modena (Italy) - Via Sallustio, 78
Tel. 059 822417 r.a. - Fax 059380281 - e-mail : info@modenacentroprove.it -
www.modenacentroprove.com
C.C.I.A.A. Modena n. 228587 - Tribunale di Modena n° 2231 C.F. e P. IVA n. 01592020364



LAB N°1018L

Membro degli Accordi di Mutuo Riconoscimento EA, IAF e ILAC

Signatory of EA, IAF and ILAC Mutual Recognition Agreements

DETERMINATION OF THE ANTI-SLIP PROPERTIES – WET-LOADED BAREFOOT AREAS; WALKING METHOD – RAMP TEST

Beginning date : 01/08/2019

Analysis ending date : 02/08/2019

SAMPLE : Ceramic tiles, marked « **STONEHENGE NATURA (SH NAT.)** »





RESULTS

Sample dimensions (length, width) : 1x0.5 m
Width of joints : 5 (mm)
Groutig substance : mortar
Direction of profiles : no one

SLIP ANGLE : 30
CLASSIFICATION : C

CLASSIFICATION

Total Average Values	Group Classification
< 12	0
≥ 12°	A
≥ 18°	B
≥ 24°	C

<p>Examiner</p>  <p>p.i. Bortolai Alberto</p>	<p>Examiner</p>  <p>p.i. Nasseti Luca</p>	<p>MODENA CENTRO PROVE</p>  <p>Ceramic Dept. Responsible P.I. De Pasquale Roberto</p>	<p>MODENA CENTRO PROVE</p>  <p>Director Sant'Unione dr. Giuseppe</p>
---	--	--	---